

## Durable Labels that Last

## 687 Clear CryoLabel® Frost Polyester

**Description:** This thin, flexible material is highly conformable making it perfect for small diameter test tubes and for fitting into the tight cavaties of vial racks and storage boxes. A smooth, gloss topcoat provides excellent print results with durable thermal transfer resin ribbons: good print results are also achieved with flexo and UV inkjet inks. The durable face offers excellent water, scratch, chemical and solvent resistance.

The adhesive exhibits excellent low temperature and cryogenic performance with good peel strength from a variety of surfaces such as polypropylene, polyethylene, polycarbonate, glass and metal. Best bonding is achieved by rubbing the label firmly.

This is a perfect label for laboratory test tube applications where you want to easily see the tube contents:

- > Works in both freezer and liquid nitrogen storage
- > Demonstrates good bonding when applied to frozen containers with light to moderate frost
- > Ideal for wrap-around label designs to over laminate printed information
- > Performs well in autoclave processes (121°C saturated steam for 30 minutes)
- > Sustains freezer-to-boiling-water cycles (LN2 <sup>2</sup> for 30 minutes then boiling water (100°C) for 10 minutes
- > Handles freezer-to-incubation cycles (-70°C for 30 minutes, CO2 incubator for 45 minutes with approximately 5% CO2)

NOTE: Due to the thin construction of this product, special die tooling may be required.

Recommended Printing Ribbons: T68, T80, T70, T182

	Face Stock	Adhesive	Liner
Туре	Polyester	Permanent	Silicone Paper
Color	Clear, Gloss	Clear	White
Caliper	1.0 mil	0.8 mil	3.2 mil
BaseWeight	-	-	55#
Min. Application Temp.	-	+10°F (-12°C)	-
Service Temp. Range	-	LN <sub>2</sub> (-321°F/-196°C) to 250°F (121°C)	-

**Storage Stability:**Shelf Life of Two Years when stored in plastic bags and kept at 70°F (21°C) with 50% R.H. (Relative Humidity)

All descriptive information, typical performance data, and recommendations for this product should be used solely as a guide. Furnishing such information is merely our attempt to assist you as indicated by your requested application. These specifications do not constitute a warranty under any varying results. All labels are sold with the understanding that the purchaser has independently tested and determined the suitability of the product for the intended application.